



Technical Datasheet

DESCRIPTION

200-c AGV PumaESD® is a low odor, **conductive**, abrasion resistant floor coating system. This 2 or 3 coat system consists of a moisture blocking primer coat (104-PumaPOXY MB), and a four-component, chemical -resistant, aliphatic polyester 112-c AGV PumaESD urethane top coat. Surface may be installed with an optional light, extra fine, glass bead finish which imparts slip resistance, but also mop cleanable.

USES:

200-c AGV PumaESD® can be installed over new concrete, and areas that have minimal substrate damage. It provides excellent resistance to abrasion and other physical aggression in manufacturing and warehouse facilities with AGV (automatic guided vehicles) or AMR (autonomous mobile robots). It handles high levels of concrete vapor emissions.AGV areas.

ADVANTAGES:

- Meets NFPA99 standards
- Extremely low, non-offensive odor.
- Consistent resistance to ground without the need of a ground plane primer utilizing conductive particulates and polymers
- BODY VOLTAGE GENERATION (BVG) below 15 volts with conductive footwear

ELECTRICAL PROPERTIES:

- Typical resistance readings would be less than 500,000 ohms.
- Meets the recommendations set forth in ANSI/ESD-S20.20-2021.
- *Resistance:* This product is capable of exhibiting surface resistance values in the static dissipative and conductive ranges in accordance to values defined in test method EOS/ESD Assn ESD STM S7.1-2005.
- Dissipates a 5000-volt charge to 0 volts in less than 0.1 seconds
- Maintains ESD properties throughout the thickness of the applied coating and not dependent humidity for proper conductivity (unlike carbon fiber systems) To assure proper contact to floor surface, persons in area protected by ESD floor coating must wear approved quality ESD footwear.

DURABILITY

Resistant to abrasion and other physical aggression from foot traffic, hand carts, and abrasion of AGV and AMR's commonly found in industrial facilities.

COMPOSITION

Non-toxic static dissipating, polyurethane resin system combined with glass bead aggregates. Complies with VOC regulations for industrial maintenance coatings in the OTC and CA.

APPEARANCE

SHEEN: Semi Gloss.

Slip Resistant: Meets ADA Standard - Coefficient of Friction (.6)

Surface is easy to clean.

MVT (Moisture Vapor Transmission)

200-c AGV PumaESD® handles high levels of MVT. Utilizing 16 mils of PumaPOXY MB primer, it blocks up to 25 lbs or MVT. This helps to protect flooring from the catastrophic effects of moisture in and below the concrete.

REPAIRABILITY

The lack of dependence on conductive fiber and ground plane primers allows this system to be repaired without sacrificing electrical performance.

APPLICATION

PumaESD® flooring is installed by certified applicators throughout the U.S.A.

SURFACE PREPARATION

To be assured of maximum adhesion and properties from any Puma-Crete® resin products the correct surface is essential. Please refer to technical data sheet "Surface Preparation".

STORAGE, MIXING & APPLICATION TEMPERATURE

The storage, mixing and application conditions can affect the quality of the finish produced. Optimum storage and application temperature are 70°F.

CURE SCHEDULE (70 deg F)

24 hours (foot traffic), 36-48 hrs Full cure (heavy traffic)

MAINTENANCE

Regular cleaning of the applied system is recommended in order to maintain slip resistant properties and cosmetics. Normal cleaning agents (such as Simple Green) w/ auto floor scrubber.

CHEMICAL RESISTANCE

Excellent resistances to organic and inorganic acids, alkalis, fuel and hydraulic oils, aromatic and aliphatic solvents.

COLORS AVAILABLE

Standard colors: Std color is Medium Gray (also available in 6 additional colors—see PumaESD color chart.

WARRANTY

5 years (refer to PUMA-CRETE® ESD warranty terms and conditions)

CONDITIONS OF USAGE:

Installation of all products purchased must be by professional installers periodically published by PUMA-CRETE or otherwise approved by PUMA-CRETE in writing. Modification to any of PUMA-CRETE's products voids the warranty. The installer shall maintain a written contemporaneous record of field conditions (including, without limitation, surface and atmospheric conditions, usage rates, and lot numbers of products installed). PUMA-CRETE reserves the right of inspection of any installed product, installation and maintenance records and records of field conditions and may conduct additional testing as is reasonably required to investigate any warranty claims. Warranty shall only apply for products or materials that have been paid for in full.

CURED PROPERTIES*: Properties	Test Method	Results
Conductivity Resistance	ANSI ESD-7.1	<500,000 ohms
Static Charge Decay	MIL-B-81705B	5000V to 0, <0.1sec
Abrasion Resistance	ASTM D4060	25 mg
Tensile Strength	ASTM D638	2600 PSI
Compressive Strength	ASTM D695	8700 PSI
Flexural Stength	ASTM D790	10,500 PSI
Hardness (shore D)	ASTM D2240	75/70
Adhesion	ACI503R	300 psi